





	Test report n.	176-QL19-R03 ver. 0	 <small>LAB N°1235</small> <small>Membro degli Accordi di Mutuo Riconoscimento EA, IAF e ILAC</small> <small>Signatory of EA, IAF and ILAC Mutual Recognition Agreements</small>
	Applicant	LARES di Claudio Lerici Regione Viazzi, 6 15010 Castelletto d'Erro (AL) - Italy	
	EUT/Type	Reflecting sheets O03, R03, W03	

TEST REPORT Nr. 176-QL19-R03 ver. 0

Addresses Indirizzi		
Applicant Richiedente	LARES di Claudio Lerici - Regione Viazzi, 6 - 15010 Castelletto d'Erro (AL) - Italy	
Manufacturer Produttore	Same as applicant / Come il richiedente	
Test laboratory Laboratorio di prova	Qualilab s.r.l. - Via Trento, 87 - 25020 - Capriano del Colle (BS) - Italy	
Dates and authorization Date e autorizzazioni		
EUT acceptance date Data accettazione campioni	Simultaneously with the beginning of the test. Contestualmente all'inizio delle prove.	
Report Date Data preparazione rapporto di prova	26/02/2019	
Authorization Autorizzazioni	Ing. Nicola Parolini Test engineer	
	Ing. Michele Peschiera Reviewer	 
Equipment under test EUT (data declared by the applicant) Dispositivo sottoposto a prova EUT (Dati forniti dal richiedente)		
EUT description Descrizione EUT	Reflecting sheets	
Type Modello	LARES O03 - amber LARES W03 - white LARES R03 - red	
Marking Marcature	-	
Applicable norms Norme applicabili		
	CIE 54.2 - Retroreflection: definition and measurement, ECE R03 and FMVSS108	



The test results and observations indicated in this test report refer exclusively to the samples tested. It is not permitted to transfer the results to other systems or configurations. The publication or duplication of this test report with enclosures, or Part of this test report or enclosures, without a written consent of the test laboratory is not permitted. The test laboratory does not assume any liability for any loss, expense or damage occasioned by the use of this report. Any use of the laboratories name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by the test laboratory. In case of a multilingual test report, the English version is the only official version.

I risultati e le osservazioni indicate in questo rapporto di prova sono riferite esclusivamente ai campioni testati. Non è permesso utilizzare i risultati e le osservazioni di questo rapporto di prova per altri sistemi o configurazioni. Non è permessa la pubblicazione o la duplicazione completa o parziale di questo rapporto di prova e dei suoi allegati senza un consenso scritto da parte del laboratorio di prova. Il laboratorio di prova non si assume responsabilità nei confronti di terzi per danni o eventuali costi derivanti dall'utilizzo dei dati presenti in questo rapporto di prova. Ogni uso del nome del laboratorio di prova e dei suoi marchi per la vendita o per pubblicizzare il prodotto testato deve essere prima approvato in forma scritta dal laboratorio di prova. In caso di rapporti di prova con più lingue, la versione inglese è da considerarsi quella ufficiale.

	Test report n.	176-QL19-R03 ver. 0	 <small>LAB N°1235</small> <small>Membro degli Accordi di Mutuo Riconoscimento EA, IAF e ILAC</small> <small>Signatory of EA, IAF and ILAC Mutual Recognition Agreements</small>
	Applicant	LARES di Claudio Lerici Regione Viazzi, 6 15010 Castelletto d'Erro (AL) - Italy	
	EUT/Type	Reflecting sheets O03, R03, W03	

Test Name Identificazione prova	Test Procedure Procedura di prova	Test Requirement Requisito di prova	Test Result Esito Prova
LARES O03	CIL measurement in accordance to CIE 54.2, ECE R03 and FMVSS108	N/A	See Appendix I
LARES W03	CIL measurement in accordance to CIE 54.2, ECE R03 and FMVSS108	N/A	See Appendix I
LARES R03	CIL measurement in accordance to CIE 54.2, ECE R03 and FMVSS108	N/A	See Appendix I

Uncertainty Incertezza	
Photometric parameter Parametri fotometrici	Coefficient of retroreflection: 3,3 % Coefficiente di retroriflessione
Statement Dichiarazione	<p>The measured value (y) and the associated expanded uncertainty (U) represent the interval ($y \pm U$) which contains the value of the measured quantity with a probability of approximately 95 % and a coverage factor $k = 2$.</p> <p>The values into the different appendix have the maximum significant figures managed by the measurement software.</p> <p>Il valore misurato (y) e l'incertezza estesa associata (U) rappresentano l'intervallo ($y \pm U$) che contiene il valore della grandezza misurata con una probabilità di circa il 95 % e un fattore di copertura $k = 2$.</p> <p>I valori negli appendici sono riportati con il massimo numero di cifre significative gestite dal software della strumentazione.</p>

	Test report n.	176-QL19-R03 ver. 0	 LAB N°1235 Membro degli Accordi di Mutuo Riconoscimento EA, IAF e ILAC Signatory of EA, IAF and ILAC Mutual Recognition Agreements
	Applicant	LARES di Claudio Lerici Regione Viazzi, 6 15010 Castelletto d'Erro (AL) - Italy	
	EUT/Type	Reflecting sheets O03, R03, W03	



APPENDIX I	LARES O03 - amber
Norm and applicable points	CIE 54.2, ECE R3 and FMVSS108
Sample identification	176-QL19-S03
Place of testing	QUALILAB s.r.l. - Via Trento, 87 - 25020 - Capriano del Colle (BS) - Italy
Test date	18/02/2019
Environmental conditions	Temperature 23 °C ± 3 °C
Instruments	Goniometer LMT GOH1200 QL-IN-002 Retro Unit LMT RETRO 2000 QL-IN-008 Datalogger TESTO 174H QL-IN-181
Test procedure	The sample was prepared, stabilized and measured like defined in ECE R03 and FMVSS08
Test requirements	n.a.
Test measurement	The sample was mounted onto the test stand, provided by the manufacturer. The sample was illuminated with standard illuminant A. The sample was installed perpendicular to the light source. Afterwards the grid, given in the ECE R03 and FMVSS108, was measured.
TEST RESULT	

ECE R03

Functions	R [mcd/lx]
0.333 at H - V	1635
0.333 at H - 10U	1624
0.333 at H - 10D	1610
0.333 at 20R - 5U	1576
0.333 at 20R - 5D	1568
0.333 at 20L - 5U	1588
0.333 at 20L - 5D	1588
1.500 at H - V	139,2
1.500 at H - 10U	132,0
1.500 at H - 10D	132,2
1.500 at 20R - 5U	133,3
1.500 at 20R - 5D	134,6
1.500 at 20L - 5U	132,5
1.500 at 20L - 5D	134,5

FMVSS108

Functions	R [mcd/lx]
0.200 at H - V	2310
0.200 at H - 10U	2300
0.200 at H - 10D	2280
0.200 at 20L - V	2260
0.200 at 20R - V	2240
1.500 at H - V	139,4
1.500 at H - 10U	131,7
1.500 at H - 10D	132,4
1.500 at 20L - V	135,8
1.500 at 20R - V	135,4

	Test report n.	176-QL19-R03 ver. 0	 <small>LAB N°1235</small> <small>Membro degli Accordi di Mutuo Riconoscimento EA, IAF e ILAC</small> <small>Signatory of EA, IAF and ILAC Mutual Recognition Agreements</small>
	Applicant	LARES di Claudio Lerici Regione Viazzi, 6 15010 Castelletto d'Erro (AL) - Italy	
	EUT/Type	Reflecting sheets O03, R03, W03	



APPENDIX II	LARES W03 - white
Norm and applicable points	CIE 54.2, ECE R3 and FMVSS108
Sample identification	176-QL19-S04
Place of testing	QUALILAB s.r.l. - Via Trento, 87 - 25020 - Capriano del Colle (BS) - Italy
Test date	18/02/2019
Environmental conditions	Temperature 23 °C ± 3 °C
Instruments	Goniometer LMT GOH1200 QL-IN-002 Retro Unit LMT RETRO 2000 QL-IN-008 Datalogger TESTO 174H QL-IN-181
Test procedure	The sample was prepared, stabilized and measured like defined in ECE R03 and FMVSS08
Test requirements	n.a.
Test measurement	The sample was mounted onto the test stand, provided by the manufacturer. The sample was illuminated with standard illuminant A. The sample was installed perpendicular to the light source. Afterwards the grid, given in the ECE R03 and FMVSS108, was measured.
TEST RESULT	

ECE R03

Functions	R [mcd/lx]
0.333 at H - V	2230
0.333 at H - 10U	2180
0.333 at H - 10D	2200
0.333 at 20R - 5U	2080
0.333 at 20R - 5D	2080
0.333 at 20L - 5U	2090
0.333 at 20L - 5D	2100
1.500 at H - V	155,1
1.500 at H - 10U	136,9
1.500 at H - 10D	135,9
1.500 at 20R - 5U	138,4
1.500 at 20R - 5D	140,1
1.500 at 20L - 5U	138,4
1.500 at 20L - 5D	140,9

FMVSS108

Functions	R [mcd/lx]
0.200 at H - V	3040
0.200 at H - 10U	2970
0.200 at H - 10D	3000
0.200 at 20L - V	2870
0.200 at 20R - V	2850
1.500 at H - V	154,6
1.500 at H - 10U	136,3
1.500 at H - 10D	136,1
1.500 at 20L - V	141,5
1.500 at 20R - V	141,7

	Test report n.	176-QL19-R03 ver. 0	 <small>LAB N°1235</small> <small>Membro degli Accordi di Mutuo Riconoscimento EA, IAF e ILAC</small> <small>Signatory of EA, IAF and ILAC Mutual Recognition Agreements</small>
	Applicant	LARES di Claudio Lerici Regione Viazzi, 6 15010 Castelletto d'Erro (AL) - Italy	
	EUT/Type	Reflecting sheets O03, R03, W03	



APPENDIX III	LARES R03 - red
Norm and applicable points	CIE 54.2, ECE R3 and FMVSS108
Sample identification	176-QL19-S05
Place of testing	QUALILAB s.r.l. - Via Trento, 87 - 25020 - Capriano del Colle (BS) - Italy
Test date	18/02/2019
Environmental conditions	Temperature 23 °C ± 3 °C
Instruments	Goniometer LMT GOH1200 QL-IN-002 Retro Unit LMT RETRO 2000 QL-IN-008 Datalogger TESTO 174H QL-IN-181
Test procedure	The sample was prepared, stabilized and measured like defined in ECE R03 and FMVSS08
Test requirements	n.a.
Test measurement	The sample was mounted onto the test stand, provided by the manufacturer. The sample was illuminated with standard illuminant A. The sample was installed perpendicular to the light source. Afterwards the grid, given in the ECE R03 and FMVSS108, was measured.
TEST RESULT	

ECE R03

Functions	R [mcd/lx]
0.333 at H - V	534
0.333 at H - 10U	481
0.333 at H - 10D	486
0.333 at 20R - 5U	456
0.333 at 20R - 5D	456
0.333 at 20L - 5U	459
0.333 at 20L - 5D	462
1.500 at H - V	54,9
1.500 at H - 10U	36,7
1.500 at H - 10D	37,5
1.500 at 20R - 5U	35,5
1.500 at 20R - 5D	36,0
1.500 at 20L - 5U	35,7
1.500 at 20L - 5D	36,1

FMVSS108

Functions	R [mcd/lx]
0.200 at H - V	695
0.200 at H - 10U	627
0.200 at H - 10D	634
0.200 at 20L - V	601
0.200 at 20R - V	597
1.500 at H - V	55,0
1.500 at H - 10U	36,6
1.500 at H - 10D	37,4
1.500 at 20L - V	36,3
1.500 at 20R - V	36,0

	Test report n.	176-QL19-R03 ver. 0	 LAB N°1235 Membro degli Accordi di Mutuo Riconoscimento EA, IAF e ILAC Signatory of EA, IAF and ILAC Mutual Recognition Agreements
	Applicant	LARES di Claudio Lerici Regione Viazzi, 6 15010 Castelletto d'Erro (AL) - Italy	
	EUT/Type	Reflecting sheets O03, R03, W03	

APPENDIX IV

Photographs

